

University of Belgrade
Technical Faculty in Bor
Mining and Metallurgy
Institute Bor



56th International
October Conference
on Mining and Metallurgy
PROCEEDINGS

Editors:

Ljubiša Balanović

Dejan Tanikić

22-25 October 2025,
Bor Lake, Serbia



PROCEEDINGS,
56th INTERNATIONAL OCTOBER CONFERENCE
on Mining and Metallurgy

Editors:

Prof. dr Ljubiša Balanović

Prof. dr Dejan Tanikić

University of Belgrade - Technical Faculty in Bor

Technical Editors:

MSc Miljan Marković

MSc Kristina Božinović

University of Belgrade - Technical Faculty in Bor

Proceedings cover design:

MSc Aleksandar Cvetković,

University of Belgrade - Technical Faculty in Bor

Publisher: University of Belgrade - Technical Faculty in Bor

For the publisher: Dean Prof. dr Dejan Tanikić

Circulation: 200 copies

Publication Place, Year: Bor, 2025

Printed by “*GRAFIKA GALEB DOO*” NIŠ, 2025

CIP - Каталогизација у публикацији Народна библиотека Србије, Београд

622(082)(0.034.2)

669(082)(0.034.2)

INTERNATIONAL October Conference on Mining and Metallurgy (56 ; 2025 ; Bor Lake)

Proceedings [Elektronski izvor] / 56th International October Conference on Mining and Metallurgy - IOC 2025, 22-25 October, 2025, Bor Lake, Serbia ; [organized by] University of Belgrade, Technical Faculty in Bor and Mining and Metallurgy Institute Bor ; editors Ljubiša Balanović, Dejan Tanikić. - Bor : University of Belgrade, Technical Faculty, 2025 (Niš : Grafika Galeb). - 1 USB fleš memorija ; 1 x 1 x 5 cm

Sistemske zahteve: Nisu navedeni. - Nasl. sa naslovne strane dokumenta. - Tiraž 200. - Preface / Ljubiša Balanović. - Bibliografija uz svaki rad.

ISBN 978-86-6305-164-5

a) Рударство -- Зборници b) Металургија -- Зборници

COBISS.SR-ID 177493257

Bor Lake, Serbia, October 22-25, 2025



The conference is financially supported by
The Ministry of Science, Technological
Development and Innovation
of the Republic of Serbia

Platinum Donors

HBIS SERBIA



Gold Sponsor



Gold Donors



Silver Donor



Exhibitions



KRUG INTERNATIONAL LTD.



Donor of official opening



Friends of the Conference



**CHINA-SERBIA
JOINT LABORATORY
ON GREEN STEEL
MANUFACTURING**

HBIS and University of Belgrade



**THE FOUNDATION
'B.SC. ENG. BOŠKO INJAC'**

SCIENTIFIC COMMITTEE

Prof. Dr Dejan Tanikić, University of Belgrade, Technical Faculty in Bor (Serbia) - president
Prof. Dr Nada Štrbac, University of Belgrade, Technical Faculty in Bor (Serbia) - vice-president
Prof. Dr Radoje Pantović, University of Belgrade, Technical Faculty in Bor (Serbia) - vice-president
Dr Ana Kostov, Mining and Metallurgy Institute Bor (Serbia) - vice-president

Prof. Dr Milan Antonijević, University of Belgrade, Technical Faculty in Bor (Serbia)
Prof. Dr Hasan Avdušinović, University of Zenica, Faculty of Engineering and Natural Sciences (Bosnia and Herzegovina)
Dr Ana Alil, University of Belgrade, Institute of Chemistry, Technology and Metallurgy (Serbia)
Prof. Dr Ljubiša Balanović, University of Belgrade, Technical Faculty in Bor (Serbia)
Prof. Dr Farzet Bikić, University of Zenica, Faculty of Engineering and Natural Sciences (Bosnia and Herzegovina)
Prof. Dr Grozdanka Bogdanović, University of Belgrade, Technical Faculty in Bor (Serbia)
Prof. Dr Pavel Broz, Masaryk University, Faculty of Science, Department of Chemistry (Czech Republic)
Dr Mile Bugarin, Mining and Metallurgy Institute Bor (Serbia)
Prof. Dr Ilhan Bušatlić, University of Zenica, Faculty of Engineering and Natural Sciences (Bosnia and Herzegovina)
Prof. Dr Nicanor Cimpoesu, Gheorghe Asachi Technical University from Iasi (Romania)
Prof. Dr Mira Cocić, University of Belgrade, Technical Faculty in Bor (Serbia)
Dr Vladan Čosović, University of Belgrade, Institute of Chemistry, Technology and Metallurgy (Serbia)
Prof. Dr Pasquale D. Cavaliere, University of Salento, Department of Innovation Engineering (Italy)
Prof. Dr Kemal Delijić, University of Montenegro, Faculty of Metallurgy and Technology (Montenegro)
Prof. Dr Nikhil Dhawan, Indian Institute of Technology, Department of Metallurgical and Materials Engineering (India)
Prof. Dr Savas Dilibal, Istanbul Gedik University, Department of Mechatronics Engineering (Turkey)
Prof. Dr Aleksandar Dimitrov, Ss. Cyril and Methodius University in Skopje, Faculty of Technology and Metallurgy (Republic of North Macedonia)
Prof. Dr Natalija Dolić, University of Zagreb, Faculty of Metallurgy (Croatia)
Prof. Dr Yong Du, Central South University Changsha (China)
Prof. Dr Luis Filipe Malheiros, University of Porto, Faculty of Engineering (Portugal)
Prof. Dr Almaida Gigović-Gekić, University of Zenica, Faculty of Engineering and Natural Sciences (Bosnia and Herzegovina)
Prof. Dr Mirko Gojić, University of Zagreb, Faculty of Metallurgy (Croatia)
Prof. Dr Adam Grajcar, Silesian University of Technology, Department of Engineering Materials and Biomaterials (Poland)
Prof. Dr Vesna Grekulović, University of Belgrade, Technical Faculty in Bor (Serbia)
Prof. Dr Daniela Grigorova, University of Chemical Technology and Metallurgy, Faculty of Metallurgy and Material Science (Bulgaria)
Prof. Dr Stojan Groudev, University of Mining and Geology "Saint Ivan Rilski" (Bulgaria)
Prof. Dr Dragoslav Gusković, University of Belgrade, Technical Faculty in Bor (Serbia)
Prof. Dr Tomaš Havlik, Institute of Recycling Technologies, Faculty of Materials, Metallurgy and Recycling, Technical University of Kosice (Slovakia)
Prof. Dr Karl Heinz Spitzer, Technical University of Clausthal, Institute for Metallurgy (Germany)
Dr Slavomír Hredzák, Institute of Geotechnics of the Slovak Academy of Sciences (Slovakia)
Prof. Dr Svetlana Ivanov, University of Belgrade, Technical Faculty in Bor (Serbia)
Prof. Dr Dejan Ivezić, University of Belgrade, Faculty of Mining and Geology (Serbia)
Mirjam Jan-Blažić, Slovenian Foundry Society (Slovenia)
Prof. Dr Dominika Jendrzeczyk-Handzlik, AGH University of Science and Technology in Kraków, Faculty of Non-Ferrous Metals (Poland)
Prof. Dr Željko Kamberović, University of Belgrade, Faculty of Technology and Metallurgy (Serbia)
Prof. Dr György Kaptay, University of Miskolc, Faculty of Materials and Metallurgical Engineering (Hungary)
Dr Vladan Kašić, Institute for Technology of Nuclear and other Mineral Raw Materials (Serbia)

Prof. Dr Vladislav Kecojević, West Virginia University (USA)
Dr Dragan Komljenović, Research Institute, Hydro-Québec (Canada)
Prof. Dr Komnitsas Konstantinos, Technical University of Crete, School of Mineral Resources Engineering (Greece)
Prof. Dr Borut Kosec, University of Ljubljana, Faculty of Natural Science and Engineering (Slovenia)
Prof. Dr Maria Krasteva, University of Chemical Technology and Metallurgy, Faculty of Metallurgy and Material Science (Bulgaria)
Prof. Dr Vladimir Krstić, Functional Materials Manufacturing, Inc. (Canada)
Prof. Dr Stefan Kuvendžiev, Ss. Cyril and Methodius University in Skopje, Faculty of Technology and Metallurgy (Republic of North Macedonia)
Prof. Dr Silvia Lavrova-Popova, University of Chemical Technology and Metallurgy, Faculty of Chemical and Systems Engineering (Bulgaria)
Dr Milenko Ljubojev, Engineering Academy of Serbia (Serbia)
Prof. Dr Xuewei Lv, Chongqing University, School of Materials Science and Engineering (China)
Prof. Dr Nedeljko Magdalinović, Engineering Academy of Serbia (Serbia)
Prof. Dr Dragan Manasijević, University of Belgrade, Technical Faculty in Bor (Serbia)
Prof. Dr Vaso Manojlović, University of Belgrade, Faculty of Technology and Metallurgy (Serbia)
Prof. Dr Boštjan Markoli, University of Ljubljana, Faculty of Natural Science and Engineering (Slovenia)
Dr Branislav Marković, Institute for Technology of Nuclear and other Mineral Raw Materials (Serbia)
Prof. Dr Desimir Marković, University of Belgrade, Technical Faculty in Bor (Serbia)
Prof. Dr Ivana Marković, University of Belgrade, Technical Faculty in Bor (Serbia)
Prof. Dr Nobuyuki Masuda, Tokyo University of Science, Faculty of Advanced Engineering (Japan)
Prof. Dr Jožef Medved, University of Ljubljana, Faculty of Natural Science and Engineering (Slovenia)
Vladan Mihailović, Executive Director for Production at HBIS Serbia (Serbia)
Prof. Dr Ivan Mihajlović, Faculty of Mechanical Engineering, University of Belgrade (Serbia)
Dr Dragan Milanović, Mining and Metallurgy Institute Bor (Serbia)
Prof. Dr Snežana Milić, University of Belgrade, Technical Faculty in Bor (Serbia)
Prof. Dr Dragan Milovanović, University of Belgrade, Faculty of Mining and Geology (Serbia)
Prof. Dr Duško Minić, University of Priština, Faculty of Technical Sciences (Serbia)
Prof. Dr Srba Mladenović, University of Belgrade, Technical Faculty in Bor (Serbia)
Prof. Dr Adnan Mujkanović, University of Zenica, Faculty of Engineering and Natural Sciences (Bosnia and Herzegovina)
Prof. Dr Cornelia Muntean, Politehnica University of Timisoara (Romania)
Prof. Dr Tatiana N. Aleksandrova, Saint Petersburg Mining University, Department of Mineral Processing (Russia)
Prof. Dr Goran Načevski, Ss. Cyril and Methodius University in Skopje, Faculty of Technology and Metallurgy (Republic of North Macedonia)
Prof. Dr Adina Negrea, Politehnica University of Timisoara (Romania)
Prof. Dr Irena Nikolić, University of Montenegro, Faculty of Metallurgy and Technology (Montenegro)
Prof. Dr Đorđe Nikolić, University of Belgrade, Technical Faculty in Bor (Serbia)
Prof. Dr Daniel Ogochukwu Okanigbe, Tshwane University of Technology, Department of Extractive Metallurgy and Mineral Processing (South Africa)
Prof. Dr Dušan Oráč, Institute of Recycling and Environmental Technologies, Faculty of Materials, Metallurgy and Recycling, Technical University of Kosice (Slovakia)
Prof. Emeritus Dr. Sc. Mirsada Oruč, University of Zenica, Faculty of Engineering and Natural Sciences (Bosnia and Herzegovina)
Prof. Dr Dimitris Panias, National Technical University of Athens, School of Mining Engineering and Metallurgy (Greece)
Prof. Dr Perica Paunović, Ss. Cyril and Methodius University in Skopje, Faculty of Technology and Metallurgy (Republic of North Macedonia)
Prof. Dr Mitar Perušić, University of East Sarajevo, Faculty of Technology Zvornik (Bosnia and Herzegovina)
Prof. Dr Batrić Pešić, University of Idaho, College of Engineering (USA)
Prof. Dr Marija Petrović Mihajlović, University of Belgrade, Technical Faculty in Bor (Serbia)
Prof. Dr Miljana Popović, University of Belgrade, Faculty of Technology and Metallurgy (Serbia)
Prof. Dr Milena Premović, University of Priština, Faculty of Technical Sciences (Serbia)
Prof. Dr Charikleia Prochaska, Aristotle University of Thessaloniki, Faculty of Sciences, School of Chemistry, Division of Chemical Technology and Industrial Chemistry (Greece)

Prof. Dr Miljana Radivojević, Institute of Archaeology, University College London (UK)
Prof. Dr Velimir Radmilović, Serbian Academy of Sciences and Arts (Serbia)
Prof. Dr Milan Radovanović, University of Belgrade, Technical Faculty in Bor (Serbia)
Prof. Dr Nenad Radović, University of Belgrade, Faculty of Technology and Metallurgy (Serbia)
Prof. Dr Žarko Radović, University of Montenegro, Faculty of Metallurgy and Technology (Montenegro)
Prof. Emeritus Karlo Raić, University of Belgrade, Faculty of Technology and Metallurgy (Serbia)
Prof. Dr Mirjana Rajčić Vujasinović, University of Belgrade, Technical Faculty in Bor (Serbia)
Dr Andrei Rotaru, University of Craiova, Department of Chemical Thermodynamics (Romania)
Prof. dr. eng. Elena Scutelnicu, "Dunarea de Jos" University of Galati, Faculty of Engineering (Romania)
Prof. Dr Snežana Šerbula, University of Belgrade, Technical Faculty in Bor (Serbia)
Dr Rustam Sharipov, JSC "Kazakh-British Technical University (Kazakhstan)
Dr Miroslav Sokić, Institute for Technology of Nuclear and other Mineral Raw Materials (Serbia)
Prof. Dr Jovica Sokolović, University of Belgrade, Technical Faculty in Bor (Serbia)
Prof. Dr Petr Solozhenkin, Russian Academy of Sciences (Russia)
Prof. Dr Dimitriu Sorin, Polytechnic University of Bucharest (Romania)
Dr Jasna Stajić Trošić, University of Belgrade, Institute of Chemistry, Technology and Metallurgy (Serbia)
Prof. Dr Velizar Stanković, University of Belgrade, Technical Faculty in Bor (Serbia)
Prof. Dr Rodoljub Stanojlović, University of Belgrade, Technical Faculty in Bor (Serbia)
Dr Jasmina Stevanović, University of Belgrade, Institute of Chemistry, Technology and Metallurgy (Serbia)
Dr Zoran Stevanović, Mining and Metallurgy Institute Bor (Serbia)
Prof. Dr Saša Stojadinović, University of Belgrade, Technical Faculty in Bor (Serbia)
Dr Srećko Stopić, RWTH Aachen University, Faculty of Georesouces and Materials Engineering (Germany)
Prof. Dr Jasmin Suljagić, University of Tuzla, Faculty of Technology (Bosnia and Herzegovina)
Dr Zhongmei Sun, Zijin Mining and Metallurgy Research Institute (China)
Dr Nadežda Talijan, Academy of Engineering Science of Serbia (Serbia)
Prof. Dr Jarmila Trpčevská, Faculty of Materials, Metallurgy and Recycling, Technical University of Kosice (Slovakia)
Dr Biserka Trumić, Mining and Metallurgy Institute Bor (Serbia)
Prof. Dr Milan Trumić, University of Belgrade, Technical Faculty in Bor (Serbia)
Dr Walter Valery, University of Queensland (Australia)
Prof. Dr Dmitry Vasilyev, A.A.Baikov Institute of Metallurgy and Materials Science, Russian Academy of Sciences (Russia)
Prof. Dr Iveta Vaskova, Faculty of Materials, Metallurgy and Recycling, Technical University of Kosice (Slovakia)
Prof. Dr Petrica Vizureanu, Gheorghe Asachi Technical University from Iasi (Romania)
Prof. Dr Tatjana Volkov-Husović, University of Belgrade, Faculty of Technology and Metallurgy (Serbia)
Prof. Dr Maja Vončina, University of Ljubljana, Faculty of Natural Science and Engineering (Slovenia)
Prof. Dr Milovan Vuković, University of Belgrade, Technical Faculty in Bor (Serbia)
Prof. Dr Nenad Vušović, University of Belgrade, Technical Faculty in Bor (Serbia)
Prof. Dr Kaikun Wang, School of Materials Science and Engineering, University of Science and Technology Beijing (China)
Prof. Dr Ridvan Yamanoglu, Kocaeli University, Engineering Faculty, Metallurgical and Materials Engineering Department (Turkey)
Prof. Dr Onuralp Yucel, Istanbul Technical University, Faculty of Chemical and Metallurgical Engineering (Turkey)
Prof. Dr Zdenka Zovko Brodarac, University of Zagreb, Faculty of Metallurgy (Croatia)

ORGANIZING COMMITTEE

Prof. Dr Ljubiša Balanović, Full Professor (UB TF Bor) – president
Prof. Dr Radoje Pantović, Full Professor (UB TF Bor) – vice-president
Dr Ana Kostov, Principal Research Fellow (MMI Bor) – vice-president

Dr Ivana Marković, Full Professor (UB TF Bor)
Prof. Dr Jovica Sokolović, Full Professor (UB TF Bor)
Dr Maja Nujkić, Associate Professor (UB TF Bor)
Dr Žaklina Tasić, Associate Professor (UB TF Bor)
Dr Milan Gorgievski, Full Professor (UB TF Bor)
Dr Ana Radojević, Associate Professor (UB TF Bor)
Dr Тања Калиновић, Associate Professor (UB TF Bor)
Dr Dejan Petrović, Associate Professor (UB TF Bor)
Dr Jelena Ivaz, Associate Professor (UB TF Bor)
Dr Anđelka Stojanović, Associate Professor (UB TF Bor)
Dr Uroš Stamenković, Assistant Professor (UB TF Bor)
Dr Jasmina Petrović, Assistant Professor (UB TF Bor)
Dr Vladimir Nikolić, Assistant Professor (UB TF Bor)

Milan Nedeljković, Assistant (UB TF Bor)
Milijana Mitrović, Assistant (UB TF Bor)
Marina Marković, Assistant (UB TF Bor)
Kristina Božinović, Assistant (UB TF Bor)
Milica Zdravković, Assistant (UB TF Bor)
Miljan Marković, Assistant (UB TF Bor)
Pavle Stojković, Assistant (UB TF Bor)
Avram Kovačević, Assistant (UB TF Bor)
Sandra Vasković, English Lecturer (UB TF Bor)
Oliver Marković, IT service (UB TF Bor)
Bojana Janković, Accountant (UB TF Bor)

LIST OF REVIEWERS

Prof. Dr Ridvan Yamanoglu, Kocaeli University (Turkey)
Prof. Dr Peizhong Feng, School Materials Science and Physics, China University of Mining and Technology (China)
Prof. Dr Srećko Stopić, IME Process Metallurgy and Metal Recycling, RWTH Aachen University (Germany)
Prof. Dr Nebojša Tadić, University of Montenegro - Faculty of Metallurgy and Technology (Montenegro)
Dr Aleksandra Mitovski, Engineering Dobersek GmbH (Germany)
Prof. Dr Žarko Radović, University of Montenegro - Faculty of Metallurgy and Technology (Montenegro)
Prof. Dr Ljubiša Balanović, University of Belgrade - Technical Faculty in Bor (Serbia)
Prof. Dr Milan Gorgievski, University of Belgrade - Technical Faculty in Bor (Serbia)
Prof. Dr Jan Vreštal, Masaryk University, Centre for Nanotechnology and Microtechnology (Czech Republic)
Prof. Dr Claire Utton, University of Sheffield, Department of Materials Science and Engineering (UK)
Prof. Dr Marija Petrović Mihajlović, University of Belgrade - Technical Faculty in Bor (Serbia)
Doc. Dr Jelena Ivaz, University of Belgrade - Technical Faculty in Bor (Serbia)
Prof. Dr Radoje Pantović, University of Belgrade - Technical Faculty in Bor (Serbia)
Prof. Dr Miodrag Banješević, University of Belgrade - Technical Faculty in Bor (Serbia)
Dr Danijel Kržanović, Mining and Metallurgy Institute Bor (Serbia)
Dr Predrag Stolić, University of Belgrade - Technical Faculty in Bor (Serbia)
Dr Vladan Marinković, Mining and Metallurgy Institute Bor (Serbia)
Prof. Dr Saša Stojadinović, University of Belgrade - Technical Faculty in Bor (Serbia)
Doc. Dr Ana Simonović, University of Belgrade - Technical Faculty in Bor (Serbia)
Doc. Dr Dejan Petrović, University of Belgrade - Technical Faculty in Bor (Serbia)
Dr Dragana Medić, University of Belgrade - Technical Faculty in Bor (Serbia)
Prof. Dr Milan Trumić, University of Belgrade - Technical Faculty in Bor (Serbia)
Prof. Dr Jovica Sokolović, University of Belgrade - Technical Faculty in Bor (Serbia)
Prof. Dr Ivana Marković, University of Belgrade - Technical Faculty in Bor (Serbia)
Prof. Dr Maja Trumić, University of Belgrade - Technical Faculty in Bor (Serbia)
Dr Dejan Todorović, Institute for Technology of Nuclear and Other Mineral Raw Materials (Serbia)
Prof. Dr Zoran Štirbanović, University of Belgrade - Technical Faculty in Bor (Serbia)
Prof. Dr Vesna Grekulović, University of Belgrade - Technical Faculty in Bor (Serbia)
Prof. Dr Dejan Tanikić, University of Belgrade - Technical Faculty in Bor (Serbia)
Prof. Dr Dominika Jendrzczyk-Handzlik, AGH University of Science and Technology in Kraków, Faculty of Non-Ferrous Metals (Poland)
Prof. Dr Grozdanka Bogdanović, University of Belgrade - Technical Faculty in Bor (Serbia)
Prof. Dr Dragan Manasijević, University of Belgrade - Technical Faculty in Bor (Serbia)
Prof. Dr Milan Radovanović, University of Belgrade - Technical Faculty in Bor (Serbia)

Dr Vesna Conić, Mining and Metallurgy Institute Bor (Serbia)
Dr Marija Korać, University of Belgrade - Faculty of Technology and Metallurgy (Serbia)
Dr Sanja Martinović, University of Belgrade - Institute of Chemistry, Technology and Metallurgy (Serbia)
Doc. Dr Uroš Stamenković, University of Belgrade - Technical Faculty in Bor (Serbia)
Dr Jasmina Petrović, University of Belgrade - Technical Faculty in Bor (Serbia)
Prof. Dr Srba Mladenović, University of Belgrade - Technical Faculty in Bor (Serbia)
Prof. Dr Saša Marjanović, University of Belgrade - Technical Faculty in Bor (Serbia)
Dr Viša Tasić, Mining and Metallurgy Institute Bor (Serbia)
Prof. Dr Junxue Zhao, School of Metallurgical Engineering, Xian University of Architecture and Technology (China)
Prof. Dr Miljana Radivojević, Institute of Archaeology, University College London (UK)
Prof. Dr Milena Premović Zečević, University of Priština, Faculty of Technical Science (Serbia)
Dr Ana Alil, University of Belgrade - Institute of Chemistry, Technology and Metallurgy (Serbia)
Prof. Dr Đorđe Nikolić, University of Belgrade - Technical Faculty in Bor (Serbia)
Prof. Dr Velimir Radmilović, University of Belgrade - Faculty of Technology and Metallurgy (Serbia)
Prof. Dr Tatjana Volkov-Husović, University of Belgrade - Faculty of Technology and Metallurgy (Serbia)
Prof. Dr Žaklina Tasić, University of Belgrade - Technical Faculty in Bor (Serbia)
Prof. Dr Tanja Kalinović, University of Belgrade - Technical Faculty in Bor (Serbia)
Dr Jelena Jordanovć, University of Belgrade - Technical Faculty in Bor (Serbia)
Prof. Dr Maja Nujkić, University of Belgrade - Technical Faculty in Bor (Serbia)
Prof. Dr Milica Veličković, University of Belgrade - Technical Faculty in Bor (Serbia)
Prof. Dr Snežana Milić, University of Belgrade - Technical Faculty in Bor (Serbia)
Dr Jelena Kalinović, University of Belgrade - Technical Faculty in Bor (Serbia)
Doc. Dr Ana Radojević, University of Belgrade - Technical Faculty in Bor (Serbia)
Dr Dragana Božić, Mining and Metallurgy Institute Bor (Serbia)
Prof. Dr Dejan Riznić, University of Belgrade - Technical Faculty in Bor (Serbia)
Dr Vaso Manojlović, University of Belgrade - Faculty of Technology and Metallurgy (Serbia)
Prof. Dr Predrag Đorđević, University of Belgrade - Technical Faculty in Bor (Serbia)
Dr Emina Požega, Mining and Metallurgy Institute Bor (Serbia)
Dr Vladan Čosović, University of Belgrade, Institute of Chemistry, Technology and Metallurgy (Serbia)
Prof. Dr Duško Minić, University of Priština, Faculty of Technical Science (Serbia)

PREFACE

On behalf of the Organizing Committee, it is a great honor and pleasure to welcome all esteemed participants of the **56th International October Conference on Mining and Metallurgy (IOC 2025)**, scheduled to take place at **Bor Lake, Serbia**, from **October 22nd to 25th, 2025**.

The collaborative efforts of the University of Belgrade – Technical Faculty in Bor and the Mining and Metallurgy Institute Bor have once again brought together academia, industry, and research institutions to organize this year's IOC. Our focus remains firmly set on presenting the latest research achievements and technological advancements in geology, mining, metallurgy, materials science, technology, environmental protection, and other engineering disciplines.

This year's conference program is rich and diverse, featuring **4 plenary lectures, 4 invited lectures, 158 full papers, and 6 abstracts**. The proceedings reflect the contributions of authors from **19 countries**: Austria, Bosnia and Herzegovina, Bulgaria, Canada, China, Croatia, Germany, Hungary, India, Mexico, Montenegro, Poland, Romania, Russia, Serbia, Slovakia, Slovenia, Turkey, and the United Kingdom. Among the submitted papers, eight young researchers under the age of 35 have qualified to participate in the “**MDPI Young Researcher Award**” competition, further emphasizing the conference's commitment to supporting and recognizing excellence among the new generation of scientists and engineers.

We are also delighted to host the **9th International Student Conference on Technical Sciences (ISC 2025)**, running in parallel with IOC 2025. The student conference brings together young researchers from Serbia and the wider region, with **one plenary** and **50 student papers** presented, offering an invaluable opportunity for the next generation of scientists and engineers to share their ideas and discuss the future of their disciplines with experts. The “**Professor Dragana Živković Best Student Paper Award**” will be presented to the most outstanding student contribution based on originality, research quality, and presentation.

The Organizing Committee expresses its deepest gratitude to all who have supported this event. Our General Sponsor is the Ministry of Science, Technological Development, and Innovation of the Republic of Serbia. We are especially grateful to our Platinum Donors, HBIS Serbia and Serbia Zijin Mining, as well as our Gold Sponsor, DPM Metals Inc., and our Gold Donors, Copper Mill Sevojno and Serbia Zijin Copper Bor. This year, the conference is also supported by the Silver Donor, “MC LABOR” d.o.o. Beograd.

We proudly host a diverse exhibition, featuring Indemak, Labtim SE d.o.o., MERIS d.o.o., Krug International LTD, Altium International d.o.o., Metalurg Foundry Ltd., Fugro Germany Land GmbH, Analysis d.o.o., Lola institut, Tescan and Mikrolux d.o.o., Trokuttest Serbia, Novos d.o.o., Changsha Rui Rui Technology Co., Ltd., MDPI and the Winery of Bukovo Monastery. The official opening of the conference has been supported by Epiroc Srbija a.d.. Finally, we warmly acknowledge our Friends of the Conference: Messer Tehnogas AD Belgrade, the China-Serbia Joint Laboratory on Green Steel Manufacturing, and the Foundation B.Sc. Boško Injac.

We sincerely thank all authors, committees, reviewers, speakers, and chairpersons for their invaluable contributions to shaping IOC 2025. We are confident that the conference will once again serve as a alive platform for scientific exchange, professional networking, and the promotion of sustainable development in mining, metallurgy, and related fields.

On behalf of the 56th IOC Organizing Committee,
Prof. dr Ljubiša Balanović




TABLE OF CONTENTS

Plenary Lectures

Markus A. Reuter (GERMANY)

Fundamental limits of green metal and mineral processing supply chains within the circular economy 3-5

Miljana Radivojević (UNITED KINGDOM)

Metals and the making of the ancient world: environmental and economic legacies of Eurasian bronze age metallurgy 6-6

Peizhong Feng, Baojing Zhang, Zhi Liu, Shiheng Li, Xiaohong Wang (CHINA)

Recycling and utilization of spent molybdenum disilicide: preparation of coating and metal recovery via synergistic smelting 7-9

Srećko Stopić, Alexander Birich, Bernd Friedrich (GERMANY)

Advances in understanding of reduction processes in extractive metallurgy 10-10

Invited Lectures

Buxin Chen, Mao Chen, Meilong Hu, Kaihui Ma, Hongqing Liu, Chenguang Bai (CHINA)

Development of hydrogen metallurgy in China 13-16

Alejandro Cruz-Ramírez, José Enrique Sanchez-Vite, Teresita del Refugio Jiménez-Romero, Margarita García-Hernández, Heriberto Mendoza-Cárdenas (MEXICO)

Characterization of industrial jarosites from the Mexican zinc extraction process 17-20

Nicanor Cimpoeșu, Ionuț Adomniței, Corneliu Munteanu, Mihai Axinte, Marian Luțcanu, Mihai Alin Pop, Marius Teleşcă, Ana Maria Roman (ROMANIA)

Characterization of ceramic coatings with thermal barrier role obtained by atmospheric plasma jet spraying 21-24

Cemalettin Okay Aksoy, Güzin Gülsev Uyar Aksoy, Hasan Berker Sarisan (TURKEY)

Computational fluid dynamics analysis of ventilation strategies for mitigating geothermal gas leakage in subsurface infrastructure projects 25-28

Conference Papers

Geology and Mining

Zoran Marković, Milić Erić, Aleksandar Milićević, Rastko Jovanović, Nikola Živković, Ivan Lazović, Milica Jovčevski (SERBIA)

Optimization of the electrostatic precipitators in unit A1 of the Kostolac a thermal power plant

33-36

Stefano Utili, Dainius Jenkus, Akanksha Mishra, Filippo Bianchi, Riccardo Castellanza (UNITED KINGDOM)

Optimal pitwall design for open pit mines in the presence of faults

37-44

Katarina M. Mihajlović, Jovica Stojanovic, Slavica Mihajlović, Ivana Jelić, Ana S. Radosavljević-Mihajlović, Suzana Erić (SERBIA)

Comparative mineralogical analysis of two zeolitic tuff Slanci and Zlatokop

45-47

Edita Lazarová, Mária Bali Hudáková, Vít'azoslav Krúpa, Alexander Kiovský, Pavol Vavrek, Lucia Ivaničová (SLOVAKIA)

Results from experimental research of rock breaking by small diameter diamond core drill bits

48-51

Edita Lazarová, Vít'azoslav Krúpa, Pavol Vavrek, Mária Bali Hudáková, Lucia Ivaničová, Alexander Kiovský (SLOVAKIA)

Failure criterion of limestone and granodiorite determined by laboratory tests and theoretical processing of drilling process results

52-55

Mária Bali Hudáková, Edita Lazarová, Vít'azoslav Krúpa, Pavol Vavrek, Lucia Ivaničová, Alexander Kiovský (SLOVAKIA)

Optimisation of the rock drilling process conducted with small diameter drilling tools

56-59

Vladan Kašić, Ana Radosavljević-Mihajlović, Jovica Stojanović, Slavica Mihajlović, Nataša Đorđević, Ivana Jelić (SERBIA)

Geological and technological characteristics of the Igroš-Vidojevići zeolite tuff deposits

60-64

Marija Jonović, Dejan Bugarin, Tanja Stanković (SERBIA)

Sensitivity analysis of a copper ore exploitation investment project using COMFAR III software

65-68

Branimir Farkaš, Ana Hrastov, Iva Štefičar (CROATIA)

Factors influencing the occurrence of flyrock phenomena on surface mines-case study

69-72

Petar Radichev (BULGARIA)

Strategic planning, design and mine management under the conditions of the Asarel open pit mine

73-76

<u>Gergana Meracheva, Efrosima Zaneva-Dobranova, Nikolay Hristov</u> (BULGARIA) <i>Geological conditions of natural H2 exploration on the Balkan peninsula for prosperity mapping</i>	77-80
<u>Güzin Gülsev Uyar Aksoy, Cemalettin Okay Aksoy, Ozan Savaş</u> (TURKEY) <i>Seismic intelligence in surface blasting: seisblast-promax as a next-generation design and optimization tool</i>	81-84
<u>Milenko Jovanović, Daniel Kržanović, Miroslava Maksimović, Vladan Marinković, Stefan Trujić, Miomir Mikić</u> (SERBIA) <i>The importance of geogrids for landfill security and environmental protection</i>	85-89
<u>Daniel Kržanović, Milenko Jovanović, Radmilo Rajković, Miljan Gomilanović, Miloš Stojanović</u> (SERBIA) <i>NPV based optimization of final pit contours in the cementacija mining complex</i>	90-93
<u>Ivica Vojinović, Dragan Šabaz, Miloš Stojanović</u> (SERBIA) <i>Implementation of the sublevel caving mining method in the T4 ore body at the Jama Bor underground mine</i>	94-97
<u>Miloš Stojanović, Ivica Vojinović, Dragan Šabaz</u> (SERBIA) <i>Application of neural networks for optimizing rock bolt system in underground mining</i>	98-101
<u>Ivica Vojinović, Miloš Stojanović, Dragan Šabaz</u> (SERBIA) <i>Technological innovations transforming the mining industry: a short review</i>	102-105
<u>Danka Kostadinović, Dušan Randelović, Zoran Marković</u> (SERBIA) <i>Implementation of ground-mounted and floating solar panels in mines</i>	106-109
<u>Milan Protić, Ana Bijelić, Miomir Raos, Marjan Popović</u> (SERBIA) <i>Kinetic modeling of oak wood thermal degradation using the distributed activation energy model (DAEM)</i>	110-114
<u>Dragan Šabaz, Ivica Vojinović, Miloš Stojanović</u> (SERBIA) <i>Monitoring techniques for subsidence induced by mining operations: a review</i>	115-118
<u>Vladan Marinković, Miroslava Maksimović, Milenko Jovanović, Željana Novaković, Andela Maričić</u> (SERBIA) <i>Geological structure and genesis of Zn, Pb deposit Ribnik-Šuplja Stijena</i>	119-122
<u>Radmilo Rajković, Vladan Marinković, Daniel Kržanović, Miomir Mikić, Milenko Jovanović</u> (SERBIA) <i>The possibility of long-term exploitation of copper ore in ore bodies of the Majdanpek copper mine</i>	123-126
<u>Miomir Mikić, Ivana Mikić, Milica Mededović, Radmilo Rajković</u> (SERBIA) <i>The global impact of climate change on the mining sector</i>	127-131

Miomir Mikić, Daniel Kržanović, Milenko Jovanović, Sandra Milutinović, Ivana Mikić (SERBIA)

The impact of climate change on mining in serbia, an overview 132-135

Milan Grozdanović, Živana Jovanović Pešić, Jelena Đoković, Dejan Tanikić (SERBIA)

Analysis of the energy potential of briquettes made from ground plum, date, and avocado pits 136-139

Milivoje Zlatić, Dejan Petrović, Jelena Ivaz, Mladen Radovanović, Milan Stajić (SERBIA)

Selection of primary support system for the river Mali Pek tunnel 140-143

Snežana Ignjatović, Branislav Petrović (SERBIA)

Applying electrical survey to detect the thickness of the Epikartst 144-147

Nikola Jovanović, Jelena Stefanović, Miloš Živanović, Zlatko Pavlović, Nikola Miljković, Jelena Đorđević, Nikola Lekić (SERBIA)

Building information modeling (BIM) as a tool for enhancing technical solutions in mining design: A case study of the main process building in Brskovo, Montenegro 148-152

Samil Hoskan, Bayram Kahraman (TURKEY)

Comparing the accuracy of Kriging and IDW interpolation for estimating a Cu-Zn deposit in Turkey 153-156

Nenad Vušović, Milica Vlahović (SERBIA)

Challenges in mining subsidence engineering 157-160

Mineral Processing and Recycling

Igor Zh. Bunin, Alexey N. Kochanov (RUSSIA)

On the mechanism of selective disintegration of rocks under explosive and pulse-discharge impacts 163-166

Renguo Li, Lanjie Li, Heng Ji, Minglei Gao, Shiwei Wang (CHINA)

Experimental study on pelletization of blended sea sand ores 167-170

Milić Erić, Zoran Marković, Aleksandar Milićević, Rastko Jovanović, Danka Kostadinović, Ivan Lazović, Milica Jovčevski (SERBIA)

Experimental research of the lignite drying process in packed bed 171-174

Slavko Todić, Predrag Lazić (SERBIA)

Investigation of the flotation potential of sulfideoxide ore from the Veliki Majdan deposit 175-178

Vladimir Nikolić, Milan Trumić (SERBIA)

Refinement of the bond work index calculation method for finer samples 179-182

Jose Enrique Sanchez-Vite, Alberto Hernandez-Casimiro, Teresita del Refugio Jiménez-Romero, Alejandro Cruz-Ramírez, Margarita García-Hernández
(MEXICO)

Mineralogical evolution in industrial jarosite through flux-assisted roasting 183-186

Albin Dobersek, Aleksandra Mitovski, Olga Mishina, Andrej Avrachov, Pavel Saltykov, Viktoriia Zhmurova, Alexandra Friesen, Theresa Schulz
(GERMANY)

Gold recovery from flotation tailings in copper metallurgy: A sustainable approach to resource valorization 187-190

Ivana Jovanović, Dragan Milanović, Vesna Conić, Miloš Janošević, Daniela Urošević, Mile Bugarin (SERBIA)

Chemical-mineralogical characterization of carbonate-clay type lithium ore 191-194

Jelena Đorđević, Jelena Stefanović, Sandra Guševac, Nevena Marković, Zoran Avramović, Nikola Jovanović, Nikola Lekić (SERBIA)

Effect of recycled asphalt (RAP) and copper slag (CS) as partial substitution of natural aggregate in asphalt mixtures 195-198

Artur Hubert, Felix Heinicke (GERMANY)

Transferring common HPGR application from copper to lithium ore 199-202

Venkateswara Rao, Jayapal Reddy (INDIA)

Mathematical modeling and statistical analysis of sub grade iron ore beneficiation using wet high intensity magnetic separator (WHIMS) 203-210

Dušica Mirović, Yuankun Yang, Shengli Yu (SERBIA)

Safety challenges in transport of copper concentrate: TML as a boundary parameter of maritime cargo stability 211-214

Klaudia Kundráková, Jana Pirošková, Jakub Klimko, Jarmila Trpčevská, Petra Růžicková, Dušan Oráč (SLOVAKIA)

Electrospinning of ZnO nanofibers from zinc galvanizing flue dust 215-220

Dragana Marilović, Grozdanka Bogdanović (SERBIA)

Leaching of covellite in ionic liquid solution 221-224

Nadezhda Kazakova, Vladislava Stefanova, Petar Iliev, Biserka Lucheva
(BULGARIA)

Analytical study of zinc recovery from spent solutions resulting after galvanization process 225-228

Katarina Balanović, Maja Trumić, Tamara Gavrilović (SERBIA)

Influence of hidden neuron number on the performance of ANN models applied to deinking flotation data 229-232

Extractive Metallurgy and Process Innovations

Teresita del Refugio Jiménez-Romero, José Enrique Sanchez-Vite, Alejandro Cruz-Ramírez, Margarita García-Hernández, Ángel de Jesús Morales-Ramírez (MEXICO)

Recovery of copper from a chalcopyrite ore using natural deep eutectic solvents (NADES) of choline chloride-urea as a leaching agent 235-238

Alexey M. Amdur, Sergei A. Fedorov (RUSSIA)

Droplet flotation in metallurgical melts 239-242

Yuchao Shi, Taibai Fu, Xinyi Zhang, Liang Zhang, Shiyi Wen, Yuling Liu, Yingbiao Peng, Jiangxing Wang, Ziqing Xie, Yong Du (CHINA)

Development of ICALPHAD software for phase diagram calculation and intelligent thermodynamic optimization 243-246

Vesna Grekulović, Milica Zdravković, Milan Gorgievski, Nada Štrbac, Miljan Marković, Marina Marković, Kristina Božinović (SERBIA)

Electrochemical behavior of copper in chloride medium in the presence of pine cone macerate 247-250

Ana Kostov, Aleksnadra Milosavljević, Ivan Jovanović (SERBIA)

DTA thermodynamic behaviour of the ternary system Ga-Ge-Sb 251-254

Dimitrije Anđić, Aleksandar Jovanović, Nikola Vuković, Ivana Jelić, Mladen Bugarčić, Vaso Manojlović, Miroslav Sokić (SERBIA)

Innovative oxidative system for leaching of Fe²⁺ from sphalerite concentrate 255-259

Vanja Trifunović, Snežana Milić, Ljiljana Avramović, Dragana Božić, Zoran Avramović (SERBIA)

Behavior of zinc, calcium and iron in the two-stage leaching process of the EAF dust 260-263

Petar Petrov (BULGARIA)

Creation of sintering cup for laboratory sintering installation 264-268

Angel Iliev, Daniela Grigorova (BULGARIA)

Thermodynamic investigation of carbothermic reduction of electric arc furnace dust 269-272

Xiaohua Liu, Renhao Tian, Yang You, Zhixiong You, Xuwei Lv (CHINA)

Numerical simulation of temperature field in a rotary hearth furnace under infrared-assisted heating conditions 273-276

Sara Lukovac, Nebojša Tadić, Dijana Đurović, Irena Nikolić (MONTENEGRO)

S/S treatment for aluminium slag waste using fly ash-based geopolymers 277-280

Xing Han, Hongqiang Liu, Lanjie Li, Pengyang Li, Xiaolong Guo (CHINA)

The role of hydrogen based shaft furnaces in steel industry decarbonization 281-286

Gvozden Jovanović, Dimitrije Andić, Danijela Smiljanjić, Dragana Randelović, Branislav Marković (SERBIA)

Behavior of plant micronutrients (Fe, Cu) during combustion of contaminated Sorghum spp.

287-290

Igor Zlatković, Živko Đorović (SERBIA)

Analysis of the new sinter line in HBIS Group Serbia and creating conditions for production improvement

291-295

Nebojša Tadić, Irena Nikolić, Nina Jovović, Dejana Dizdar, Vanja Asanović, Milena Tadić (MONTENEGRO)

Valorization of fly ash and plastic waste using geopolymerization technology

296-299

Miloš Vuleta, Milodarka Žugić, Vladan Andrejić, Tamara Ristić (SERBIA)

Industrial optimization of BOF steelmaking: increasing scrap ratio through hot metal parameter control

300-303

Milivoje Zlatić, Dejan Petrović, Jelena Ivaz, Mladen Radovanović, Milan Stajić (SERBIA)

Artificial intelligence challenges in modern alloy design

304-307

Vesna Conić, Miloš Janosević, Dragan Milanović, Ivana Jovanović, Daniela Urošević, Mile Bugarin (SERBIA)

Overview of methods for bor separation

308-311

Sandra Guševac, Nevena Marković, Jelena Đorđević, Jelena Stefanović (SERBIA)

The possibility of using copper slag aggregate in concrete

312-315

Emine Sayılğan, Patrick Zhang (TURKEY)

Leaching behaviour of phosphogypsum with different acids

316-318

Duško Minić, Milena Zečević, Aleksandar Đorđević, Veljko Minić (SERBIA)

Electrical resistivity of the Al-Bi-Ge ternary alloys

319-322

Velizar Stanković, Miljan Marković, Milan Gorgievski, Stefan Đordjević (SERBIA)

On the leachability of copper from copper-iron minerals mixture

323-326

Ferenc Kristaly, László Farkas, Andrea Mihalkó, Bence Tamás, Balázs Szeleczki (HUNGARY)

Recoverable Pd and Pt accumulation in a Ca(OH)₂ based CO₂ filter of a hydrogenation organic byproduct plant

327-330

Oliver Dimitrijević, Ivana Jovanović, Vesna Conić, Dragan Milanović, Tanja Stanković (SERBIA)

Example of dense media cyclone selection

331-334

Petra Ružičková, Klaudia Kundráková, Kristína Talianová, Jakub Klimko, Dušan Oráč (SLOVAKIA)

Selective recovery of copper from hydrometallurgical processing of e-waste 335-340

Alloys, Composites, and Advanced Materials

Anca Cazac, Diana-Petronela Burduhos-Nergis, Andrei Victor Sandu, Mihai Popa, Costica Bejinariu (ROMANIA)

Strontium phosphate conversion coatings: A short review 343-346

Maja Vončina, Jožef Medved, Tinkara Smolar, Matej Steinacher (SLOVENIA)

Influence of heat treatments on mechanical properties of aluminium alloy EN AW-2011 347-350

Alexandra Tamara Sutic, Gheorghe Bădăraș, Romeu Chelariu, Ramona Cimpoeșu, Ana-Maria Roman, Mihai-Adrian Bernevig, Nicanor Cimpoeșu (ROMANIA)

An assessment of corrosive and mechanical performance of biodegradable ZnMgTi alloys 351-354

Jožef Medved, Tilen Balaško, Stanislav Kores, Maja Vončina (SLOVENIA)

In-situ synthesis of Mg₂Si-reinforced amc 355-359

Karlo T. Raić, Mile B. Đurđević, Srećko Manasijević, Aleksandra Patarić, Marija Mihailović (SERBIA)

Statistical evolution of non-metallic inclusions in continuous cast Al-killed steel 360-363

Kristina Božinović, Dragan Manasijević, Ljubiša Balanović, Milan Gorgievski, Uroš Stamenković, Miljan Marković (SERBIA)

Microstructural analysis and thermal properties of Ag-Sn alloys 364-370

Srdan Matijašević, Mirko Grubišić, Nataša Đorđević, Ana Radosavljević-Mihajlović, Slavica Mihajlović (SERBIA)

The effect of the free energy change on crystallization in lithium-germanate glass 371-374

Jovana Ružić, Jelena Stašić, Marko Simić, Andrijana Žekić, Branislava Vučetić, Dušan Božić (SERBIA)

Influence of the heat treatment on the structural parameters of the CuCrZr-TiB₂ alloy 375-377

Ionuț Adomnitei, Daniela Lucia Chicet, Bogdan Istrate, Marcelin Benchea, Gheorghe Bădăraș, Nicanor Cimpoeșu (ROMANIA)

Obtaining and characterization of high yttria content in zirconia coatings 378-381

Florin Sorin Todirică, Daniela Lucia Chicet, Dragoș-Cristian Achiței, Vasile Manole, Mihai-Adrian Bernevig, Ioan Stirbu, Nicanor Cimpoeșu (ROMANIA)

Using energy dispersive spectroscopy for a stainless steel-brass welding interface characterization 382-385

Shehret Tilvaldyev, América Yamile Amaya Diaz, Adrian Alberto Castro De La Cruz (CANADA)

Analysis of the variations of the wing lift coefficient of unmanned aerial vehicles with increasing Reynolds number of airflow

386-389

Nebojša Tadić, Žarko Radović (MONTENEGRO)

Investigation of the influence of residual stresses on the mechanical properties of aluminum alloy strips

390-393

Aida Imamović, Mirsada Oruč, Milenko Rimac, Gorazd Kosec, Safet Hamedović (BOSNIA AND HERZEGOVINA)

Influence of dimensional size of rolled product made of S690QL steel on impact toughness and grain size

394-400

Krzysztof Pancikiewicz, Mariusz Maslak, Paulina Zajdel, Marcin Klimek (POLAND)

Phase transformations in a welded joint of unalloyed steel after long-term subcritical annealing

401-404

Franjo Kozina, Zdenka Zovko Brodarac, Ivica Buljeta, Natalija Dolić (CROATIA)

Analysis of crack formation in AlSi11 alloy automotive rim

405-408

Žaklina Tasić, Marija Petrović Mihajlović, Ana Simonović, Milan Radovanović, Milan Antonijević (SERBIA)

Carbon-based electrochemical sensor modified with metal oxide nanoparticles

409-412

Almaida Gigović-Gekić, Elvis Agović, Hasan Avdušinović, Branka Muminović (BOSNIA AND HERZEGOVINA)

Testing the impact of toughness of the welded joint of steel S21800

413-416

Lovro Liverić, Tamara Holjevac Grgurić, Marko Kršulja, Matej Fonović (CROATIA)

TEM Investigation of Cu-10Al-7Ag Shape Memory Alloy in As-Cast State

417-420

Marko Kršulja, Damir Karabaić, Lovro Liverić, Samir Grudić (CROATIA)

Comparison of non-destructive and destructive welding assessment tests on MAG-welded AISI316L and DH36 steels using K-309LT filler

421-425

Dana Bolibruchová, Martina Sýkorová, Marek Matejka (SLOVAKIA)

Influence of Be addition on mechanical and physical properties of alloys with low Si content

426-429

Milan Nedeljković, Srba Mladenović, Vladan Čosović, Ivana Marković, Jasmina Petrović, Uroš Stamenković, Milijana Mitrović, Avram Kovačević (SERBIA)

Microstructures and wettability behavior of Sn-0.7Cu solder doped with graphene nanosheets

430-433

<u>Srba Mladenović, Nikola Marinković, Dragica Milojković, Jasmina Petrović, Milan Nedeljković (SERBIA)</u> <i>Structural characterization of welded joints of AlSiMg alloys</i>	434-437
<u>Martina Sýkorová, Dana Bolibruchová, Marek Matejka (SLOVAKIA)</u> <i>Development of the Al-Si alloy with niobium addition for gigacastings</i>	438-441
<u>Veljko Savić, Vladimir Topalović, Jelena Nikolić, Marija Došić, Milena Obradović, Danijela Smiljanić, Snežana Grujić (SERBIA)</u> <i>Insights into the glass network structure of coal fly ash-based glass</i>	442-445
<u>Uroš Stamenković, Ivana Marković, Dragan Manasijević, Milan Nedeljković (SERBIA)</u> <i>Termomechanical treatment of S275JR steel: impact on microstructure, hardness, and impact toughness</i>	446-449
<u>Milan Protić, Momir Prašević, Nikola Mišić, Mimir Raos, Viša Tasić (SERBIA)</u> <i>Flammability assessment of acoustic insulation materials using mass loss calorimetry</i>	450-453
<u>Marek Matejka, Dana Bolibruchová, Martina Sýkorová (SLOVAKIA)</u> <i>Analysis of selected properties of Al-Si-Cu based alloy with tungsten addition</i>	454-457
<u>Žarko Mišković, Radivoje Mitrović, Danilo Pejčić, Jovana Antić (SERBIA)</u> <i>Overview of installations and methodologies for conveyor idlers testing-developed at the Faculty of Mechanical Engineering at the University of Belgrade</i>	458-461
<u>Mile B. Đurđević, Srećko Manasijević, Aleksandra Patarić, Marija Mihailović, Karlo Raić (SERBIA)</u> <i>Role of magnesium in solidification feeding of hypoeutectic Al-Si5-Mg alloys</i>	462-465
<u>Jelena Gligorijević Sokolović, Jasmina Petrović, Emina Požega (SERBIA)</u> <i>Casting of bronze castings with thin walls using wax-paraffin models and CO₂ hardened sand molds</i>	466-469
<u>Shi Wenli, Tanja Marinković Stojanović, Aleksandar Djuga, Marko Radosavljević, Stefan Nešić (SERBIA)</u> <i>Metallurgical and process challenges in flash butt welding of different dimensions of micro-alloyed steel on continuous pickle line</i>	470-473
<u>Emina Mededović, Vanja Asanović, Milena Tadić, Jasmina Grbović Novaković, Irena Nikolić, Anđela Mitrović Rajić (MONTENEGRO)</u> <i>Structural changes in pyrophyllite induced by mechanochemical modification and zinc oxide doping</i>	474-477
<u>Biljana Zlatičanin, Branislav Radonjić (MONTENEGRO)</u> <i>Effect of copper content on phase formation and mechanical response of Al-Cu alloys</i>	478-481

Biljana Zlatičanin, Branislav Radonjić (MONTENEGRO)

Combined effect of cooling conditions and Mg content on the microstructure and properties of Al-15Cu alloys

482-485

Vladimir Glushchenkov (RUSSIA)

Improvement in the technology of pouring copper plates for their further use in electrolysis production

486-489

Marko Pavlović, Marina Dojčinović, Mirjana Stojanović (SERBIA)

Cavitation resistance of talc-reinforced pyrophyllite ceramics

490-493

Salko Ćosić, Almir Osmanović, Jasmin Halilović (BOSNIA AND HERZEGOVINA)

Probabilistic analysis of press fit joint load carrying capacity

494-497

Saša Marjanović, Milijana Mitrović, Emina Požega, Dragana Božić (SERBIA)

Influence of cold rolling and annealing on the hardness of Cu-Al bimetallic strip

498-501

Emina Požega, Slavko Bernik, Dragana Božić, Srđana Magdalinović, Miloš Đukić, Jelena Gligorijević Sokolović, Radmilo Rajković (SERBIA)

Properties of Se doped Bi₂Te₃ based material: Part I

502-505

Nandita Gupta, Kamlesh Kumar Singh, Manoj Kumar, Himanshu Khandelwal (INDIA)

A study of single piece ceramic shell core for geometrically complex investment casting

506-510

Veljko Minić, Jelena Miladinović, Miljana Popović, Milena Zečević, Aleksandar Đorđević (SERBIA)

Experimental characterization of the Bi-Ge-Pb ternary alloys

511-514

Ondrej Kožej, Iveta Vasková, Ladislav Jankovčín (SLOVAKIA)

Investigation of gas and shrinkage porosity in AlSi10Mg alloy gearbox castings manufactured by HPDC

515-521

Jasmina Petrović, Srba Mladenović, Uroš Stamenković, Milan Nedeljković, Milijana Mitrović (SERBIA)

Effect of oxy-cutting on the microstructure and hardness of high-carbon steel

522-525

Ivana Marković, Uroš Stamenković, Dragan Manasijević, Ljubiša Balanović (SERBIA)

Changes in hardness and microstructure during isothermal aging of nickel-aluminum bronze

526-529

Ferenc Kristály, László Farkas, Andrea Mihalkó, Bence Tamás, Balázs Szelecski (HUNGARY)

Microscale features of Pd-Pt aggregates resulted from aniline hydrogenation tar incinerating process

530-533

<u>Sandra Milutinović, Ljubiša Obradović, Sanja Petrović, Srdana Magdalinović, Ivana Mikić (SERBIA)</u> <i>Reinforcements in composite materials</i>	534-537
<u>Milijana Mitrović, Saša Marjanović, Biserka Trumić, Milan Nedeljković, Jasmina Petrović, Uroš Stamenković (SERBIA)</u> <i>Influence of temperature and annealing time on changes of the mechanical properties of the CuFe1 alloy</i>	538-541
<u>Zoran Karastojković, Radiša Perić, Srba Mladenović (SERBIA)</u> <i>Limitations for wider usage of gold-aluminium alloys based on intermetallic compound Au-Al₂</i>	542-545
<u>Dragan Jeremić, Željko Šutović, Milić Ječmenica, Dragomir Glišić, Stefan Dikić, Nenad Radović (SERBIA)</u> <i>Development of 12.0mm thick hot rolled strip of S640MC grade steel in HBIS Serbia</i>	546-549
<u>Technology and Energy</u>	
<u>Margarita García-Hernández, Alejandro Cruz-Ramírez, Ángel de Jesús Morales-Ramírez, José Enrique Sanchez-Vite, Teresita del Refugio Jiménez-Romero (MEXICO)</u> <i>Decay time determination from luminescence emissions of Eu³⁺ doped Y₂O₃ powder</i>	552-555
<u>Valery Pierre Vassiliev, Cristopher Stanley (RUSSIA)</u> <i>Optimization of heat capacities of sphalerite and wurtzite phases as a single system</i>	556-559
<u>Rastko Jovanović, Ivan Lazović, Milić Erić, Zoran Marković, Marija Živković (SERBIA)</u> <i>Predicting CO emissions using novel numerical model for particle ignition/combustion</i>	560-563
<u>Marija Jeremić, Andreas Krammer, Markus Lehner (AUSTRIA)</u> <i>Biomass to BioSNG-Methanation of syngas from biomass gasification</i>	564-567
<u>Duško Kostić, Mitar Perušić, Srećko Stopić, Dragan Kostic, Jelena Vuković, Nebojša Vasiljević, Radislav Filipović, Vladimir Damjanović (BOSNIA AND HERZEGOVINA)</u> <i>High-pressure oxygen leaching of tionite residue for titanium recovery</i>	568-574
<u>Zoran Avramović, Dragana Božić, Vanja Trifunović, Jelena Stanković (SERBIA)</u> <i>Cathodic protection of metals</i>	575-578
<u>Milica Zdravković, Slađana Savić, Vesna Grekulović, Dalibor Stanković, Iva Dimitrievska (SERBIA)</u> <i>ATR-FTIR characterization of the white willow bark extract used as a copper corrosion inhibitor</i>	579-582

Milica Zdravković, Edina Huseinović, Jasmina Dedić, Emir Horozić, Vesna Grekulović (SERBIA)

Extraction of bioactive compounds from nettle seeds as a potential inhibitor of metal corrosion

583-587

Milica Zdravković, Slađana Savić, Vesna Grekulović, Dalibor Stanković (SERBIA)

HPLC-DAD identification of compounds in corrosion inhibitor Salix Alba bark extract and the hydrolate

588-592

Milos Đukić, Stefan Đordievski, Sanela Vasiljević, Dragana Adamović-Marković, Emina Požega, Jelena Nikolić, Vesna Stankov-Jovanović (SERBIA)

Internal quality control of ICP-MS method for water analysis

593-596

Environmental Protection, Remediation and Risk Assessment

Aleksandar Grigorov, Silviya Lavrova, Daniela Grigorova (BULGARIA)

Application of nanomaterials in water treatment from manganese

599-602

Ana Marinković, Jovana Buha Marković, Jasmina Savić, Milica Mladenović, Milić Erić, Zoran Marković, Biljana Vučićević (SERBIA)

Assessment of mercury content in different fuel types

603-606

Marija Koprivica, Marija Simić, Jelena Petrović, Jelena Dimitrijević, Marija Ercegović, Marija Marković (SERBIA)

Tree leaf biochar as a potential adsorbent for lead ion removal from aqueous solution

607-610

Vesna Krstić, Danijela Simonović, Renata Kovačević, Daniel Kržanović, Mirjana Šteharnek, Daniela Urošević, Sunčica Stanković (SERBIA)

Multivariate statistical evaluation of agricultural soil contamination near the city of Bor

611-615

Ana Petrović, Stefan Đordievski, Miloš Đukić, Emina Požega, Jelena Gligorijević Sokolović, Dragana Adamović-Marković (SERBIA)

Application of metal foams for the water purification process

616-619

Viša Tasić, Tatjana Apostolovski-Trujić, Renata Kovačević, Bojan Radović, Nevena Ristić (SERBIA)

State of air quality in the city of Bor in 2024

620-623

Aleksandra Papludis, Slađana Alagić, Snežana Milić, Dragana Medić, Jelena Nikolić, Snežana Jevtović, Ivana Zlatanović Đaić (SERBIA)

Distribution of PAHs in soils from Bor region, taken from the rooting zone of poison ivy

624-627

Žarko Radović, Nebojša Tadić (MONTENEGRO)

Effect of air oxygen enrichment on gaseous fuels combustion and GHG emission

628-631

<u>Maja Nujkić, Žaklina Tasić, Sonja Stanković, Dragana Medić (SERBIA)</u> <i>Optimizing cadmium ion adsorption: predictive modeling based on literature data</i>	632-635
<u>Miljan Marković, Milan Gorgievski, Marina Marković, Vesna Grekulović, Nada Štrbac, Kristina Božinović, Milica Zdravković (SERBIA)</u> <i>Statistical modeling of copper ions biosorption onto sunflower hulls</i>	636-640
<u>Miloš Stojanović, Nicoleta Sorina Nemes, Adina Negrea, Mihaela Ciopec, Ivan Svrkota, Daniel Kržanović, Igor Svrkota (SERBIA)</u> <i>Environmental sampling strategy for the Romania–Serbia border mining region</i>	641-644
<u>Danka Kostadinović, Milić Erić, Ivan Iazović (SERBIA)</u> <i>Application of waste materials in green roofs</i>	645-648
<u>Branislava Matić, Snežana Živković Perišić, Srđan Mančević (SERBIA)</u> <i>Use of AIRQ+ software in assessing the impact on health from exposure to particles in Bor, Serbia</i>	649-654
<u>Jelena Kalinović, Tanja Kalinović, Ana Radojević, Snežana Šerbula, Jelena Jordanović (SERBIA)</u> <i>Assessment of element accumulation efficiency in plant parts using biological factor analysis</i>	655-658
<u>Milan Gorgievski, Marina Marković, Miljan Marković, Vesna Grekulović, Nada Štrbac, Kristina Božinović, Milica Zdravković (SERBIA)</u> <i>Equilibrium and thermodynamic analysis of the adsorption of copper ions on sunflower hulls</i>	659-663
<u>Marina Marković, Milan Gorgievski, Miljan Marković, Vesna Grekulović, Nada Štrbac, Kristina Božinović, Milica Zdravković (SERBIA)</u> <i>Kinetic analysis of copper ions adsorption on sunflower hulls</i>	664-668
<u>Danijela Šimonović, Daniel Kržanović, Renata Kovačević, Daniela Urošević, Mirjana Šteharnik, Sunčica Stanković, Vesna Krstić (SERBIA)</u> <i>Assessment of heavy metal contamination of soil and the ecological risk based on national limit values and quantitative indices</i>	669-673
<u>Aleksandra Petrović, Stefan Đordiević, Bojan Radović, Renata Kovačević (SERBIA)</u> <i>Assesment of PAH and PCB concentrations in Bor River bed sediments affected by mining and metallurgy</i>	674-677
<u>Stefan Đordiević, Ana Radojević, Tanja Kalinović, Maja Nujkić, Jelena Kalinović, Jelena Jordanović, Renata Kovačević, Yasumasa Ogawa (SERBIA)</u> <i>Assessment of the copper availability by extraction of riverbed sediments from Eastern Serbia with 0.5 M HCl</i>	678-681

Miloš Đukić, Stefan Đordievski, Sanela Vasiljević, Dragana Adamović-Marković, Ana Petrović, Jelena Nikolić, Vesna Stankov-Jovanović (SERBIA)

Cerovo river-Annual monitoring of impact of the Cerovo open-pit mine

682-685

Emine Sayilgan, Patrick Zhang (TURKEY)

A review on recovery of REEs and radioactive materials from phosphogypsum

686-688

Industrial Management, Digitalization and Quality Control

Yufei Wang, Xiaoyu Zheng, Xiangyang Ying, Qi Huang, Xiong Shuai, Changfa Du, Ya Li, Yingbiao Peng, Yuling Liu, Yong Du (CHINA)

Integrated computational material engineering practice paths by Changsha Ruirui Technology: From CALPHAD to phase field and crystal plastic finite element

691-694

Aleksandra Fedajev, Sanela Arsić (SERBIA)

Is mining and quarrying most efficient and profitable export sector in Serbia? Insights from a multi-criteria performance analysis

695-699

Predrag Stolić, Zoran Jovanović, Željko Mravik, Marko Jelić, Sonja Jovanović, Aleksandra Milosavljević (SERBIA)

The path to better education of engineers using open data-A practical example in the Republic of Serbia

700-703

Tatjana Volkov Husović, Ana Alil, Sanja Martinović (SERBIA)

NDT methods for monitoring degradation of refractory lining for blast furnace and converter

704-711

Maria Krasteva, Petar Raykov (BULGARIA)

Quality control in the production of vacuum pumps for the automotive industry

712-715

Andelka Stojanović, Isidora Milošević, Dragan Manasijević (SERBIA)

Intra- and extra-EU trade in recyclable metals: opportunities for industrial symbiosis

716-720

Marijana Pavlov-Kagadejev, Aleksandra Milosavljević (SERBIA)

Application of metaheuristic algorithms in metallurgical industry: A review of methods and applications

721-724

Abstracts

Eugeniu Martac, Christine Laskov, Katarzyna Staniewska (GERMANY)

Mining after mining: Real-time XRF-CPT for strategic resource estimation in tailings reprocessing

727-727

Tilen Balaško, Aleš Nagode, Jiehua Li, Jožef Medved, Maja Vončina (SLOVENIA)

The role of lanthanum addition in the microstructural evolution of an EN AW-7175 alloy during solution annealing

728-728

<u>Wei Su, Yi Xing, Yang Zheng, Rongrong Lei (CHINA)</u> <i>Construction and technological progress of a comprehensive carbon reduction system for CCUS in the steel industry</i>	729-729
<u>Stefan Trujić, Miroslav Popović, Milenko Jovanović, Katarina Milivojević, Boško Vuković (SERBIA)</u> <i>Geological investigations of the 'Povlatna zona' and 'Istočno polje' of the Gacko Coal Basin (BiH) for coal quality assessment and design of a beneficiation plant (2023–2025)</i>	730-730
<u>Roxana Hobjâlă, Nicolae Răzvan Mititelu, Ștefana Agop, Laurențiu Slătineanu, Diana Diaconu (ROMANIA)</u> <i>The contribution and application of polymeric materials in the metallurgical industry</i>	731-731
<u>Ștefana Agop, Bogdan-Ionut Dochita, Roxana Hobjâlă, Nicanor Cimpoeșu, Tiberiu Sutic (ROMANIA)</u> <i>The behavior description of CuZnAl shape memory alloys through the dynamics of multifractal complex systems</i>	732-732
Publishing partners	733-738
Donors	739-772
Author Index	773-780

KINETIC MODELING OF OAK WOOD THERMAL DEGRADATION USING THE DISTRIBUTED ACTIVATION ENERGY MODEL (DAEM)

Milan Protić^{1a}, Ana Bijelić^{1b}, Miomir Raos^{1c}, Marjan Popović^{2a}

¹ Faculty of Occupational Safety, University of Nis, Carnojevice 10A, 18000 Nis, Serbia

² Miphem, Matice Srpske 57e, 11000 Belgrade, Serbia

^{1a} milanprotic@gmail.com, 0000-0003-4957-7882

^{1b} ana.bijelic@znrfak.ni.ac.rs, 0000-0002-8073-1641

^{1c} miomir.raos@znrfak.ni.ac.rs, 0000-0001-5586-0276

^{2a} marjan@miphem.rs, 0009-0001-7621-9346

Abstract

This study investigates the thermal degradation behavior of oak wood using non-isothermal thermogravimetric analysis (TGA) under inert conditions. The Distributed Activation Energy Model (DAEM) was applied to model the pyrolysis kinetics, capturing the complex decomposition of lignocellulosic components. The pre-exponential factor, mean activation energy, and standard deviation were determined by fitting the DAEM to experimental data. The model showed excellent agreement with the observed TGA curve, achieving a high coefficient of determination ($R^2 = 0.9834$). The results highlight the dominance of hemicellulose degradation in early pyrolysis stages and demonstrate the suitability of DAEM for representing the thermal behavior of hardwood biomass. The derived kinetic parameters offer valuable input for reactor design and simulation in bioenergy applications.

Keywords: oak wood, pyrolysis, thermal degradation, DAEM, kinetic modeling, TGA

1. INTRODUCTION

The increasing demand for renewable energy sources has positioned biomass, such as oak wood, as a critical component in the transition towards a sustainable energy future. Thermochemical conversion processes, including pyrolysis, gasification, and combustion, are the primary pathways for transforming this solid feedstock into valuable energy and chemical products. The design, optimization, and scaling of reactors for these processes depend fundamentally on a precise understanding of the material's thermal degradation behavior. In this context, kinetic studies are indispensable, as they provide the essential parameters (activation energy and pre-exponential factor) that quantify the reaction rates governing the decomposition process. These parameters serve as vital inputs for robust process modeling and simulation. However, modeling the kinetics of biomass is challenging. Oak wood is a heterogeneous composite of hemicellulose, cellulose, and lignin, each degrading through complex and overlapping reactions over a wide temperature range. Consequently, simpler kinetic approaches are often not adequate. Model-fitting methods, for example, which assume a single reaction mechanism for the entire process, are a significant oversimplification that can yield parameters with limited physical meaning. Model-free (isoconversional) methods, such as the Ozawa-Flynn-Wall (OFW) [1,2] and Kissinger-Akahira-Sunose (KAS) [3,4] models, represent an improvement as they do not assume a reaction model and can show how the effective activation energy varies with the extent of conversion. Despite this advantage, they typically do not provide a complete kinetic model capable of accurately reconstructing the original experimental data from the derived parameters. The Distributed Activation Energy Model (DAEM) provides a more physically realistic and powerful framework. DAEM presumes that the complex overall reaction is a superposition of countless independent, parallel, first-order reactions, where the activation energies are not a single value but follow a statistical distribution, typically Gaussian [5]. This approach elegantly captures the energetic

heterogeneity of the biomass components. The primary merit of DAEM is that it yields a complete and compact “kinetic triplet” (the pre-exponential factor (A), the mean activation energy (E_0), and the standard deviation of the distribution (σ)). This triplet constitutes a full kinetic model that can be used to accurately predict the material’s degradation behavior, offering a robust method for model validation [6]

Therefore, the aim of this study is to apply the DAEM to non-isothermal thermogravimetric analysis (TGA) data to determine the complete kinetic triplet for the pyrolysis of oak wood and to validate the model’s accuracy in describing its complex thermal degradation process.

2. EXPERIMENTAL

2.1 Material and Thermogravimetric Analysis (TGA)

The feedstock material used in this study was oak wood (*Quercus* sp.). The sample was prepared by drying at 105°C for 24 hours to remove moisture, then milling and sieving to obtain a particle size fraction of < 100 μm .

The thermal degradation behavior of the oak wood sample was investigated using a Perkin Elmer TGA 4000 (Norwalk, CT, USA). A sample mass of approximately 10 mg was placed in a ceramic crucible. The analysis was conducted under a nitrogen atmosphere with a constant flow rate of 20 mL/min to ensure an inert environment and prevent thermo-oxidative degradation. The sample was heated from 30°C to 900°C at a constant heating rate (β) of 5°C/min. The instrument recorded the sample mass as a function of time and temperature. The resulting data provides the basis for the kinetic analysis.

2.2 Kinetic Modeling: The Distributed Activation Energy Model (DAEM)

To describe the complex kinetics of oak wood pyrolysis, the Distributed Activation Energy Model (DAEM) was employed. The thermal degradation of lignocellulosic biomass, such as oak wood, is not a single-step reaction. It is a complex process involving the simultaneous and overlapping decomposition of its primary components: hemicellulose, cellulose, and lignin. Each of these components degrades through a multitude of chemical reactions. Simpler kinetic models, like single-step model-fitting methods, fail to capture this inherent complexity and can lead to kinetic parameters that lack true physical meaning. The DAEM provides a more physically realistic framework by assuming that the overall pyrolysis process consists of an infinite number of independent, parallel, first-order reactions. Each of these reactions is characterized by its own activation energy, E . The central concept of DAEM is that these activation energies are not discrete values but are continuously distributed around a mean value, following a statistical probability distribution function, $f(E)$. The overall conversion rate at any given time or temperature is the sum of the rates of all these individual reactions. The rate of a single first-order reaction can be described by the Arrhenius equation:

$$\frac{d\alpha}{dt} = A \cdot \exp\left(-\frac{E}{RT}\right) \cdot (1 - \alpha)$$

where: α is the conversion fraction; t is time (s); A is the pre-exponential factor (s^{-1}); E is the activation energy (J/mol); R is the universal gas constant (8.314 J/mol·K) and T is the absolute temperature (K).

The conversion, α , is defined based on the mass loss measured during TGA:

$$\alpha = \frac{m_0 - m_t}{m_0 - m_f}$$

where m_0 , m_t , and m_f are the initial, instantaneous, and final mass of the sample, respectively.

Derivation expressed here follow exposition provided in [5]. For a non-isothermal process with a constant heating rate, $\beta = dT/dt$, the rate equation can be integrated to find the conversion for a single reaction with activation energy E :

$$1 - \alpha(T, E) = \exp\left(-\frac{A}{\beta} \int_{T_0}^T \exp\left(-\frac{E}{RT'}\right) dT'\right)$$

To obtain the total conversion for the entire material, this expression is integrated over the distribution of activation energies, $f(E)$:

$$1 - \alpha(T) = \int_0^\infty \exp\left(-\frac{A}{\beta} \int_{T_0}^T \exp\left(-\frac{E}{RT'}\right) dT'\right) \cdot f(E) dE$$

It is commonly assumed, and has been shown to be effective for biomass, that the activation energies follow a Gaussian distribution:

$$f(E) = \frac{1}{\sigma\sqrt{2\pi}} \exp\left(-\frac{(E - E_0)^2}{2\sigma^2}\right)$$

This distribution is defined by two key parameters: the mean activation energy (E_0) and the standard deviation (σ). The standard deviation, σ , represents the width of the distribution and is an indicator of the energetic heterogeneity of the reacting components. A larger σ value implies a more complex material with a wider range of simultaneous reactions. The goal of the DAEM analysis is to determine the three kinetic parameters (A , E_0 , and σ) that best describe the experimental TGA data. This “kinetic triplet” provides a complete and physically meaningful description of the thermal degradation process. In this work, the kinetic triplet was determined by fitting the DAEM equation to the experimental TGA data using a non-linear least-squares optimization algorithm implemented in Python. The algorithm minimizes the sum of the squared differences between the experimental conversion values (α_{exp}) and the model-predicted values (α_{pred}).

3. RESULTS AND DISCUSSION

The thermal decomposition of the oak wood sample under an inert nitrogen atmosphere was investigated using thermogravimetric analysis (TGA) and its derivative (DTG) curve. Figure 1 shows the TG and DTG curves, which represent the percentage of mass loss and the corresponding mass loss rate as functions of temperature. An initial mass loss of approximately 3% below 100 °C corresponds to moisture evaporation and the release of light volatiles. This is followed by a major decomposition stage between 235 and 360 °C, attributed to the breakdown of structural polymers. Above 360 °C, mass loss continues at a slower rate due to the pyrolysis of more stable compounds, resulting in approximately 11% char residue at 900 °C. The DTG curve exhibits a sharp peak around 355 °C (cellulose degradation), a shoulder near 285 °C (hemicellulose), and a broad tail above 400 °C (lignin), reflecting the complex nature of lignocellulosic pyrolysis. Hemicellulose decomposes first, overlapping with cellulose, while lignin degrades gradually starting around 200 °C. Cellulose and hemicellulose primarily contribute to volatile product formation, whereas lignin is mainly responsible for char production [7].




Figure 1. Thermogravimetric (TG, solid line) and derivative thermogravimetric (DTG, dashed line) curves of oak tree biomass obtained during thermal analysis in an inert nitrogen atmosphere at a heating rate of 5 °C/min.

The experimental data was fitted to the Distributed Activation Energy Model (DAEM) to obtain a comprehensive kinetic description of the pyrolysis process. The obtained kinetic parameters are: Pre-exponential Factor (A): $1.00 \times 10^8 \text{ s}^{-1}$; Mean Activation Energy (E_0): 131.23 kJ/mol and Standard Deviation (σ): 15.64 kJ/mol. The model yielded a coefficient of determination (R^2) of 0.9834, indicating a strong correlation between the experimental data and the DAEM-predicted curve, confirming the model's suitability for describing the overall process. The mean activation energy (E_0) of 131.23 kJ/mol is a particularly interesting result. This value is lower than the overall activation energy typically reported for the bulk pyrolysis of hardwoods, which often falls in the 170-200 kJ/mol range [6,8]. However, it is highly characteristic of the thermal degradation of hemicellulose. This suggests that the DAEM fit, while modeling the entire conversion curve, has identified the initial, lower-temperature decomposition of hemicellulose as the dominant energetic barrier controlling the onset and early stages of pyrolysis for this oak wood sample. The pre-exponential factor (A) is correspondingly lower than many values reported for bulk biomass pyrolysis. This is consistent with the kinetic compensation effect, a phenomenon where a lower activation energy is mathematically compensated by a lower pre-exponential factor to describe a given reaction rate. The combination of a lower E_0 and A accurately models the observed reaction, particularly in the crucial low-temperature regime. The standard deviation (σ) of 15.64 kJ/mol quantifies the width of the energy distribution. This value reflects the inherent heterogeneity of the material, accounting for the overlapping reactions of not just hemicellulose, but also the initial stages of cellulose and lignin degradation that occur within this energetic spectrum. The robustness of the derived kinetic triplet was validated by comparing the TGA curve predicted by the model against the experimental data across the entire temperature range. As shown in Figure 2, the DAEM curve closely follows the experimental data in the main pyrolysis region but slightly deviates above 400 °C, where the model predicts a faster decline than observed experimentally.




Figure 2. Weight lost curve (left) and conversion profile (right) for oak wood pyrolysis, illustrating model accuracy (experimental TGA curve (blue) and DAEM fit (orange))

The successful application of the DAEM provides a reliable kinetic model for oak wood pyrolysis. The obtained kinetic triplet serves as a compact and physically meaningful tool for predicting the material's thermal behavior.

Obtained DAEM parameters reveal that the oak sample was energetically easy to decompose, as its transformation during the early pyrolysis phase was largely influenced by less energetic routes. The main devolatilization window (ca. 235–360 °C) with a DTG peak near 355 °C and a lower-temperature shoulder around 285 °C aligns with hemicellulose–cellulose overlap. Residual char of $\approx 11\%$ at 900 °C also falls in the expected hardwood range. To compare our results with those from the literature, we referred to an international round-robin study on beech wood [6]. That study, which fitted three parallel reactions (cellulose, hemicellulose, lignin), reported component activation energies of approximately 150 kJ mol⁻¹ for hemicellulose and ca. 180 kJ mol⁻¹ for cellulose. The standard deviations were moderate (ca. 8–15 kJ mol⁻¹), while lignin showed markedly higher and less stable values at high conversion. Cai et al. used a three-parallel DAEM and found peaks centered near 178 kJ mol⁻¹ (xylan) and 210 kJ mol⁻¹ (cellulose), with narrow σ for cellulose and broader distributions for lignin, reflecting component heterogeneity [8]. Taken together, our single-Gaussian $E_0 = 131$ kJ mol⁻¹ is lower than the component-wise DAEM means commonly reported for hardwoods. This can be attributed to the model fit being most constrained by the initial, dominant mass loss from low-energy hemicellulose pathways, which are averaged with less-emphasized, high-temperature reactions in the single-distribution DAEM.

4. CONCLUSION

This study applied the Distributed Activation Energy Model (DAEM) to non-isothermal TGA of oak wood (*Quercus* sp.) and produced a compact kinetic triplet (A , E_0 , σ) that accurately reconstructed the experimental TG curve. The parameters ($A = 1.00 \times 10^8$ s⁻¹, $E_0 = 131.23$ kJ mol⁻¹, $\sigma = 15.64$ kJ mol⁻¹) indicate that early, lower-barrier pathways dominate conversion under the present conditions. This is consistent with a prominent hemicellulose contribution in the main devolatilization regime. When contrasted with DAEM studies on hardwoods, our E_0 lies below typical literature means for component-resolved fits. This difference can be attributed to (i) the single-distribution representation and (ii) the emphasis on the major mass-loss window.

ACKNOWLEDGEMENTS

This work is supported by the Ministry of Science, Technological Development and Innovation of the Republic of Serbia pursuant to agreement № 451-03-137/2025- 03/200148 with the University of Niš, Faculty of Occupational Safety and ERASMUS+ Jean Monnet Module “Workplace and Process Safety in Next Generation Europe - Teaching for Learning”.

REFERENCES

- [1] J.H. Flynn, L.A. Wall, J. Polym. Sci. B., 4 (5) (1966) 323-328.
- [2] T. Ozawa, Bull. Chem. Soc. Jap., 38(11) (1965) 1881-1886.
- [3] H.E. Kissinger, Anal. Chem., 29(11) (1957) 1702-1706.
- [4] S. Vyazovkin, Thermochim. Acta, 355(1-2) (2000) 155-163.
- [5] K. Miura, ENFL, 9(2) (1995) 302-307.
- [6] A. Anca-Couce, C. Tsekos, S. Retschitzegger, F. Zimbardi, A. Funke, S. Banks, N. Kienzl, Fuel, 276 (2020) 118002.
- [7] M. Protic, A. Miltojevic, M. Raos, P. Đekić, Facta Univ., Work. Living Environ. Prot., (2020) 135-145.
- [8] J. Cai, W. Wu, R. Liu, G.W. Huber, Green Chem., 15(5) (2013) 1331-1340.